

PRODUCT DESCRIPTION

MXBON® 14518 is designed for the sealing of gaskets. The product is a single component anaerobic, acrylic based product. The product cures when confined in the absence of air between close fitting metal surfaces. It seals close fitting joints between flanges and fixed metal faces and will flex with minor movement from the flange.

Technology	Acrylic
Chemical Type	Methacrylate ester
Appearance (uncured)	Red gel
Fluorescence	Positive under UV
Components	One component – requires no mixing
Viscosity	High, thixotropy
Cure	Anaerobic
Cure Benefit	Room temperature cure
Application	Gasketing and sealing
Technology	Acrylic

NSF International


Registered to NSF Category S2 for use as a sealant where there is no possibility of food contact in and around food processing areas. Note: This is a regional approval. Please contact your local Technical Service Center for more information and clarification.

TYPICAL PROPERTIES OF UNCURED MATERIAL


Specific Gravity @ 25 °C	1.1
Flash Point -	See SDS
Viscosity, Brookfield - HBT, 25 °C, mPa·s (cP)	
Spindle TC, 5 rpm	500,000 to 1000,000
Shelf life	24 months unopened when stored at 8 to 24°C

TYPICAL CURING PERFORMANCE**Cure Speed vs. Substrate**


The rate of cure will depend on the substrate used. The graph below shows the shear strength developed with time on grit blasted steel lap shears compared to different materials and tested according to ISO 4587.

**Cure Speed vs. Temperature**

The rate of cure will depend on the temperature. The graph below shows the shear strength developed with time at different temperatures on grit blasted steel lap shears and tested according to ISO 4587.

**Cure Speed vs. Activator**

Where cure speed is unacceptably long, or large gaps are present, applying activator to the surface will improve cure speed. The graph below shows the shear strength developed with time on grit blasted steel lap shears using Activator 017649 and tested according to ISO 4587.



Adhesive Properties

Cured for 24 hrs @ 25°C

Lap Shear Strength, ISO 4587:

Bonding Identical Substrate	N/mm ²	psi
Steel	4.3	626
Aluminum	0.2	33

Cured for 1 week @ 25 °C Lap Shear Strength, ISO 4587:

Bonding Identical Substrate	N/mm ²	psi
Steel	4.4	636
Aluminum	1.6	228

Cured for 30 minutes @ 25°C, Compressive Shear Strength, ISO 10123:


Bonding Identical Substrate	N/mm ²	psi
Steel pins and collars	7.0	1,015

Cured for 24 hours @ 25°C, Compressive Shear Strength, ISO 10123:

Bonding Identical Substrate	N/mm ²	Psi
Steel pins and collars	7.7	1,117

Heat Aging

Aged at temperature indicated and tested @ 25°C

**Chemical/Solvent Resistance**

Aged under conditions indicated and tested @ 25°C

Environment	Temp. °C	% of initial strength					
		168 hrs	500 hrs	1000 hrs	3000 hrs	5000 hrs	
Unleaded Petrol	25	20	15	10	10	5	
Water/ethylene glycol 50/50	87	150	130	110	100	90	
IPA	25	100	100	100	100	95	
Acetone	25	80	70	60	55	50	

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be used with chlorine or other strong oxidizing materials. Where washing systems are used to clean the surfaces before bonding, it is important to check the compatibility of the washing solution with the adhesive. In some cases, these solutions can affect the cure and performance of the adhesive. This product is not recommended for use on certain plastics. Users are recommended to confirm compatibility of the product with such substrates.

Storage & Handling precaution

Keep adhesive in a cool and dry place. The storage temperature is recommended at 8 °C to 24 °C. For details, consult the Safety Data Sheet, (SDS). Shelf life is two years from the date of manufacture in the original container under the optimal conditions.

1. Avoid contact with skin and eyes.
2. If contact with skin, rinse with water.
3. If adhesive gets into eye, keep eye open and rinse with water thoroughly. Seek medical attention immediately.
4. Keep the material out of children's reach.

Directions for use

For assembly

1. The substrate surfaces must be clean and free of grease.
2. Shake the product thoroughly before use.
3. If the cure speed is too slow, consider using activator.
4. Apply several drops to the nut & bolt.
5. Assemble and tighten as required.
6. To prevent the clogging of the bottle nozzle, do not let the tip touch the metal surfaces during application.

For disassembly & cleanup

1. Use localized heat (250 °C) to nut and bolt, disassemble while hot.
2. Use a wire brush to clean the charred product.

Note

The data contained herein are furnished for informational purposes only and are believed to be reliable. However, Cartell Chemical Co., Ltd does not assume responsibility for any results obtained by persons over whose methods Cartell Chemical Co., Ltd has no control. It is the user's responsibility to determine the suitability of Cartell Chemical Co., Ltd's products or any production methods mentioned herein for a particular purpose, and to adopt such precautions as may be advisable for the protection of property and persons against any hazards that may be involved in the handling and use of any Cartell Chemical Co., Ltd's products. Cartell Chemical Co., Ltd specifically disclaims all warranties express or implied, including warranties of merchantability or suitability for a particular purpose arising from sale or use of Cartell Chemical Co., Ltd's products. Cartell Chemical Co., Ltd further disclaims any liability for consequential or incremental damages of any kind including lost profits.